



VerdeFloor RT

Rake & Trowel Applied Heavy-Duty Polyurethane Concrete

TECHNICAL DATA SHEET

TECHNOLOGY DESCRIPTION

VerdeFloor flooring systems represent the next generation of polyurethane concrete technology. These Bio-Based flooring systems utilize domestically produced soy bean oil and environmentally friendly packaging.

PRODUCT DESCRIPTION

VerdeFloor RT is a Heavy-Duty seamless flooring system typically installed at 1/4 - 3/8" in thickness. VerdeFloor RT is extremely tough and withstands thermal shock, impact, abrasion and chemical exposure. VerdeFloor RT is formulated with a natural additive to be resistant to Fungi Growth per the industry standard ASTM G-21.

TYPICAL PROPERTIES AT 70°F

Compressive Strength (ASTM C-579)	7,800 psi
Tensile Strength (ASTM C-307)	975 psi
Flexural Strength (ASTM C-580)	1,900 psi
Bond Strength (ASTM D-4541)	100% Concrete Failure
Impact Strength, in/lbs (ASTM D-4226)	>160 in-lb
VOC	5 gm/l
Resistance to Fungi Growth (ASTM G-21)	Passes, Rating of 1

The data shown above reflects typical results based on laboratory testing under controlled conditions. Variations from the data shown may result. Test methods are modified where applicable.

INSTALLATION DATA

Application Temperature, ambient	40–85°F
Application Temperature, material	50–80°F
Shelf Life	6 months
Pot Life, @ 77°F	15 minutes
Traffic, @ 77°F	Light: 12 hours / Full: 24 hours
Fully Cured, @ 77°F	7 days

Refer to VerdeFloor Application Guide for additional installation information

IMPORTANT INFORMATION

1. VerdeFloor RT is not color stable, expect color change over time.
2. VerdeFloor flooring should not be installed on wet concrete.
3. Floors should be sloped to drain to prevent standing water or chemicals.
4. Spills should be removed as soon as possible to prevent a slipping hazard.
5. Confirm product performance in specific chemical environment prior to use.
6. Prepare substrate according to "Surface Preparation" portion of this document.
7. Follow detailed instructions in the "VerdeFloor Application Guide"
8. Always use protective clothing consistent with OSHA regulations during use.
9. Refer to Safety Data Sheet for detailed safety precautions.
10. For industrial/commercial use. Installation by trained personnel only.

BENEFITS

- Seamless, hygienic finish; no grout joints
- Impact & abrasion resistant surface suitable for heavy traffic and fork lift operation
- Low odor, fast installation, fast cure
- Excellent corrosion & chemical resistance
- High temperature resistant to 250 F
- Thermal shock resistant; steam cleanable
- Resistant to moisture vapor transmission (MVT)
- Anti-slip surface, meets ADA recommendations
- Resistant to fungi growth per ASTM G-21

RECOMMENDED USES

- Food & beverage processing facilities
- Chemical process facilities
- Pharmaceutical facilities
- Pulp and paper mills
- Wet processing & packaging areas
- Commercial Kitchens
- Freezers and coolers
- Battery charging areas
- Truck unloading areas

GENERIC DESCRIPTION

Polyurethane Concrete

TYPICAL APPLICATION

1/4" Trowel applied monolithic Floor

AVAILABLE COLORS

Red, Dark Red, Gray, Dark Gray, Tan, Green, Blue, Light Blue, Safety Yellow

PACKAGING & COVERAGE

1/2 Gallon Part A, 1/2 Gallon Part B

1 RT Filler Bag

1 Powder Pigment

20 sqft/unit for a 1/4" finished floor

SURFACE PREPARATION

Concrete: Apply only to properly prepared clean, dry and sound concrete substrates that are free of all coatings, sealers, curing compounds, oils, greases or any other contaminants.

- *New concrete should ideally be cured for a minimum of 14 days to reduce possible shrinkage cracking in the concrete. VerdeFloor can be installed after 7 days or when concrete reaches a minimum 3,500 psi compressive strength which will allow for proper surface preparation, however, early curing movement, shrinkage or cracking that may occur in the concrete will be reflected through the final VerdeFloor flooring.*
- *Concrete that has been contaminated with chemicals or other foreign matter must be neutralized or removed.*
- *Remove any laitance or weak surface layers including broom finish surface.*
- *Concrete should have a minimum surface tensile strength of at least 300 PSI per ASTM D-4541.*
- *Surface profile shall be CSP-5 or greater meeting ICRI (International Concrete Repair Institute) standard guideline #03732 for coating concrete, producing a profile equal to 40-grit sandpaper or coarser. Prepare surface by mechanical means to achieve this desired profile.*
- *All concrete surface irregularities, cracks, expansion joints, control joints and terminations should be properly addressed and prepared prior to application of the flooring. Moving joints and cracks will reflect through the final installed VerdeFloor flooring.*

Refer to “VerdeFloor Application Guide” for more details.

INSTALLATION STEPS

IMPORTANT – Follow the detailed application instructions in the “VerdeFloor Application Guide” and the safety instructions listed on the product Safety Data Sheets (SDS) copies available upon request. The following installation summary is for reference only and should not be relied upon as all inclusive. VerdeFloor systems should only be installed by trained persons experienced in polyurethane concrete flooring applications.

1. To prevent lifting or delamination, keyways (minimum 5/16" wide x 5/16" deep) must be cut at all terminations, joints, columns, doorways, and drains. See VerdeFloor construction detail drawings.
2. Clean sand and dust from prepared concrete where the floor is to be installed.
3. VerdeFloor CB Cove Base material can be used to install a cove and/or base as required. The cove/base can be installed before or after the installation of the VerdeFloor RT depending on the specification and or the desired result. The VerdeFloor CB can be used to create a simple cant cove as well.
4. It is very important to utilize a proper mixer and paddle to ensure a complete mix and to reduce the risk of introducing excessive air into the mixture. Verdia recommends the use of a MAN-U-FAB M-61 (1 HP) mixer with a 10 gallon pail and TR4-10 mixing arm. (www.mixall.com)
5. With the mixer running, pour ½ Gallon Part A into the mixing pail.
6. Add 1 Powder Pigment bags to Part A and mix for about 15 seconds.
7. Add ½ Gallon Part B, mix another 15 seconds.
8. Gradually add all contents of a bag of VerdeFloor RT filler into the liquid mixture and blend thoroughly until all particles are wetted out, normally about two minutes.
9. Immediately after mixing (within 3 minutes), spread the mixed VerdeFloor RT onto the floor at a thickness slightly greater than the desired finish, using a screed box or move by hand trowel.
10. Trowel the surface lightly, using a steel finish trowel to smooth the surface. Finish trowel strokes should all be in the same direction. Do not overwork the mortar. The material should be troweled to a finished thickness of at least 1/4" to 3/8", for thicknesses greater than 1" add 25 lbs. of clean, dry 3/8" pea gravel to the mixture to help reduce the heat generated during cure.
11. Immediately roll the surface lightly with a spiked roller. Excessive rolling or use of loop roller will reduce slip resistance.
NOTE: Late or heavy rolling may induce pinholes.
12. Lay abutting edges within 10 minutes to ensure a clean edge. A “wet edge” installation is imperative during large placements to avoid lines and ridges in the finished floor.

© Copyright 2015 Verdia. All rights reserved. Published technical data and instructions are subject to change without notice.

Please contact Verdia for the most current technical data, safety data and application instructions.

Rev 09/15

Verdia, warrants its products to be free from defects in material and workmanship. Verdia's sole obligation and Buyer's exclusive remedy in connection with the products shall be limited, at Verdia's option, to either replacement of products not conforming to this warranty or credit to Buyer's account in the invoiced amount of the nonconforming products. Any claim under this Warranty must be made by Buyer to Verdia in writing within five days of Buyer's discovery of the claimed defect, but in no event later than the expiration of the applicable shelf life, or one year from the delivery date, whichever is earlier. Buyer's failure to notify Verdia of such nonconformance as required herein shall bar Buyer from recovery under this warranty.

Verdia makes no other warranties concerning this product. No other warranties, either expressed or implied, or statutory, such as warranties of merchantability or fitness for a particular purpose, shall apply. In no event shall Verdia be liable for consequential or incidental damages.

Any recommendation or suggestion relating to the use of the products made by Verdia, whether in its technical literature, or in response to specific inquiry, or otherwise, is based on data believed to be reliable; however, the products and information are intended for use by Buyers having requisite skill and know-how in the industry, and therefore it is for the Buyer to satisfy itself of the suitability of the products for its own particular use, and it shall be deemed that Buyer has done so, at its sole discretion and risk. Variation in environment changes in procedures of use, or extrapolation of data may cause unsatisfactory results. Verdia cannot guarantee that color will conform to sample, if provided.